

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. (Currently amended) A white-emitting LED with a defined color temperature, designed as a luminescence conversion LED, comprising:

a primary radiation source, which is a chip that emits in the blue spectral region;

a layer of ~~two~~ first and second phosphors in front of said source, both of which phosphors partially convert the radiation of the chip;

wherein the first phosphor is from the class of the oxynitridosilicates having a cation M and the empirical formula $M_{(1-c)}Si_2O_2N_2:D_c$, where M comprises Sr as the main constituent and D is doped with divalent Europium, $M = Sr$ or $M = Sr_{(1-x-y)}Ba_yCa_x$ with $0 \leq x+y < 0.5$ being used, the oxynitridosilicate completely or predominantly comprising ~~the~~ a high-temperature-stable modification HT; and

wherein the second phosphor is a nitridosilicate of formula $(Ca,Sr)_2Si_5N_8:Eu$, producing a color temperature of from 2300 to 7000 K and at the same time achieving a color rendering of at least $Ra = 80$.

2. (Previously presented) The LED as claimed in claim 1, wherein in the oxynitridosilicate the Eu fraction makes up between 0.1 and 20 mol% of M.

3. (Previously presented) The LED as claimed in claim 1, wherein a proportion of M, in particular up to 30 mol%, is replaced by Ba and/or Ca and/or Zn.

4. (Previously presented) The LED as claimed in claim 1, wherein a proportion of M, in particular up to 30 mol%, is replaced by Li and/or La and/or Na and/or Y.

5. (Currently amended) The LED as claimed in claim 1, wherein a proportion of the SiN group in the empirical formula for said first phosphor, ~~in particular up to 30 mol%~~, is replaced by AlO.

6. (Currently amended) The LED as claimed in claim 1, wherein a proportion of Eu, ~~in particular up to 30 mol%~~, is replaced by Mn.

7. (Previously presented) The LED as claimed in claim 1, wherein the chip is an InGaN chip.

8. (Previously presented) The LED as claimed in claim 1, wherein the LED is dimmable.

9. (Previously presented) The LED as claimed in claim 1, wherein the LED has a color temperature of from 2700 to 3300 K.

10. (Currently amended) The LED as claimed in claim 1, wherein the LED achieves the white luminous color by color mixing with the RGB principle, with the primary emission of the blue LED having a peak wavelength of from 430 to 470 nm.

11. (Currently amended) The LED as claimed in claim 10, wherein the emission from the chip has a peak wavelength in the range from 450 to 465 nm.

12. (Previously presented) The LED as claimed in claim 1, wherein the emission of the oxynitridosilicate has a dominant wavelength λ_{dom} in the range from 550 to 570 nm.

13. (Previously presented) The LED as claimed in claim 1, wherein the nitridosilicate contains Sr as a permanent component, and Ca in a proportion of from 0 to 60 mol%.

14. (Previously presented) The LED as claimed in claim 1, wherein the emission of the nitridosilicate has a dominant wavelength λ_{dom} in the range from 620 to 660 nm.

15. (Previously presented) The LED as claimed in claim 1, wherein an Ra of at least 85 is achieved.

16. (Previously presented) An illumination system having the LED as claimed in claim 1, wherein the system includes electronics for driving the individual LEDs or groups of LEDs.

17. (Previously presented) The illumination system as claimed in claim 16, wherein the electronic control includes means which impart dimmability.

18. (New) The LED as claimed in claim 5, wherein the proportion of the SiN group in the empirical formula for said first phosphor replaced by AlN is up to 30 mol %.

19. (New) The LED as claimed in claim 6, wherein the proportion of Eu replaced by Mn is up to 30 mol %.